



## General data

Panel	2200 x 190 mm
Total thickness	14 mm
Numbers of panels per pack	6
m <sup>2</sup> per pack	2,508 m <sup>2</sup>
Kg per pack	27,37 kg

## Panel build up

Toplayer	PEFC controlled sources	EN 13489	± 3 mm
Core board	PEFC controlled sources		Spruce
Backing layer	PEFC controlled sources	Spruce	2 mm
Tongue and groove	Length		Uniclic
	Width		Uniclic Multifit

## Warranty

Domestic use	Conditions in each pack	33 years
Uniclic - Multifit connection		Lifetime
Commercial		On request

## Surface layer

Wood species			Oak
Origin			Europe
Finishing	UV cured Oiled finish		2 layers
	UV cured Lacquer	Anti-scratch top coat	5 - 7 layers
Natural variance	Due to nature, visual surface can deviate from samples		
"Reclaimed" look	Handsanded surface with saw cuts, where limited height differences and gaps are allowed		
Surface treatments	cf catalogue/website		

## Grading

According to EN 13489:2002 Free Class

	Nature	Marquant	Vibrant
	<i>Face of the element</i>		
Sound sapwood	Permitted, colour stained	Permitted, colour stained	Permitted, colour stained
Knots	Permitted if max 20 mm fully filled	Permitted if max 50 mm half or fully filled	Permitted if max 80 mm half or fully filled
Checks/Cracks	Not permitted	Permitted if Closed Crack ≤ 1/2 of the plank	Permitted unlimited
Bark pockets	Not permitted	Not permitted	Not permitted
Lightning shake	Not permitted	Not permitted	Not permitted
Grain structure	Grain width ≤ 80 mm	Unlimited	Unlimited
Sound heart	Permitted	Permitted	Permitted
Colour variation	Mild natural variation	Lively variation	Very lively variation
Stick marks	Not permitted	Not permitted	Not permitted
Medullary ray	Permitted	Permitted	Permitted
Biodeterioration	Not permitted	Not permitted	Not permitted
	<i>Non-visible parts</i>		
	All features permitted without any limitation as to size or quantity if these do not impair the strength or wearing quality of the parquet flooring		

Installation		Norm requirements		Quick-Step values
Floating		On Quick-Step underlay	cf installation instructions	
Glued to subfloor		Quick-Step MS polymer resin	cf installation instructions	
General aspect of installed flooring	EN 13489	Lipping - difference in height (mm)	≤ 0,20	≤ 0,15
		difference in width (mm)	≤ 0,20	≤ 0,15
		cupping lengthwise %	≤ 0,1	≤ 0,1
		cupping in width %	≤ 0,2	≤ 0,2
Dimensional stability	ISO 24339	Cupping short side max %	≤ 0,30	≤ 0,25
	Changes 30 - 85 % RH	Cupping short side min %	≥ - 0,20	≥ - 0,15
		Open joints short side (mm)	≤ 0,20	≤ 0,15
		Open joints long side (mm)	≤ 0,30	≤ 0,20
Underfloor heating	Suitable	cf special installation instructions		

#### Classification properties

Wear resistance	SIS 923509	Falling sand		800 - 1000
	DIN 68861	S 33		100 - 1050
Stain resistance	EN 13442		All except blue ink	class 5
			Blue ink	class 3
CE	EN 14342:2013	notified body	0766 EPH Dresden	DOP QW 0507
Castor chairs	ISO 4918	Tested with underlay		25.000
Slip resistance	CEN/TS 15676 : 2008	Dry Pendulum test	Depending on structure and surface treatment	USRV 37-57
Emission of formaldehyde	EN 717-1			≤ E1
PCP	CEN/TR 14823:2004			≤ 5 ppm
Heat resistance	EN 12664: 2001			0,14 m <sup>2</sup> .K/W
Reaction to fire	EN 13501-1			Dfl-s1

#### Ecological certificates

AFFSET	A	France
PEFC	PEFC/07-32-37	
EPD	On request	
Higieniczny	HK/B/0149/03/2017	Poland

