



General data

Panel	1820 x 190 mm
Total thickness	14 mm
Numbers of panels per pack	6
Nested Lengths	Max. 1 plank out of 6
m ² per pack	2,075 m ²
Kg per pack	17,32 kg

Panel build up

Toplayer	PEFC controlled sources	EN 13489	± 3 mm
Core board	PEFC controlled sources		Spruce
Backing layer	PEFC controlled sources	Spruce	2 mm
Tongue and groove	Length		Uniclic
	Width		Uniclic Multifit

Warranty

Domestic use	Conditions in each pack	33 years
Uniclic - Multifit connection		Lifetime
Commercial		On request
Edge Protect +	Provides a warranty on build-up of residue dirt along the edges due to maintenance over the years	10 years
Surface & Edge Protect + (lacquered products only)	Provides a warranty on pollution of surface structure and a warranty on build-up residue dirt along the edges due to maintenance over the years	10 years

Surface layer

Wood species			Oak
Origin			Europe
Finishing	UV cured Oiled finish	2 layers	
	UV cured Lacquer	Anti-scratch top coat	5 - 7 layers
Natural variance	Due to nature, visual surface can deviate from samples		
Surface treatments	cf catalogue/website		

Grading

According to EN 13489:2002 Free Class			
	Nature	Marquant	Vibrant
Face of the element			
Sound sapwood	Permitted, colour stained	Permitted, colour stained	Permitted, colour stained
Knots	Permitted if max 20 mm fully filled	Permitted if max 50 mm half or fully filled	Permitted if max 80 mm half or fully filled
Checks/Cracks	Not permitted	Permitted if Closed Crack ≤ 1/2 of the plank	Permitted unlimited
Bark pockets	Not permitted	Not permitted	Not permitted
Lightning shake	Not permitted	Not permitted	Not permitted
Grain structure	Grain width ≤ 80 mm	Unlimited	Unlimited
Sound heart	Permitted	Permitted	Permitted
Colour variation	Mild natural variation	Lively variation	Very lively variation
Stick marks	Not permitted	Not permitted	Not permitted
Medullary ray	Permitted	Permitted	Permitted
Biodeterioration	Not permitted	Not permitted	Not permitted
Non-visible parts			
All features permitted without any limitation as to size or quantity if these do not impair the strength or wearing quality of the parquet flooring			

Installation		Norm requirements		Quick-Step values
Floating		On Quick-Step underlay	cf installation instructions	
Glued to subfloor		Quick-Step MS polymer resin	cf installation instructions	
General aspect of installed flooring	EN 13489	Lipping - difference in height (mm)	≤ 0,20	≤ 0,15
		difference in width (mm)	≤ 0,20	≤ 0,15
		cupping lengthwise %	≤ 0,1	≤ 0,1
		cupping in width %	≤ 0,2	≤ 0,2
Dimensional stability	ISO 24339 Changes 30 - 85 % RH	Cupping short side max %	≤ 0,30	≤ 0,25
		Cupping short side min %	≥ - 0,20	≥ - 0,15
		Open joints short side (mm)	≤ 0,20	≤ 0,15
		Open joints long side (mm)	≤ 0,30	≤ 0,20
Underfloor heating	Suitable	cf special installation instructions		

Classification properties

Wear resistance	SIS 923509	Falling sand	800 - 1000	
	DIN 68861	S 33	100 - 1050	
Stain resistance	EN 13442	Floors with Edge Protect+	All except blue ink	class 5
			Blue ink	class 3
		Floors with Surface Protect + (Lacquered only)		class 5
CE	EN 14342:2013	notified body	0766 EPH Dresden	DOP QW 0507
Castor chairs	ISO 4918	Tested with underlay		25.000
Slip resistance	CEN/TS 15676 : 2008	Dry Pendulum test	Depending on structure and surface treatment	USRV 37-57
Emission of formaldehyde	EN 717-1	≤ E1		
PCP	CEN/TR 14823:2004	≤ 5 ppm		
Heat resistance	EN 12664: 2001	0,14 m ² .K/W		
Reaction to fire	EN 13501-1	Dfl-s1		

Ecological certificates

AFFSET	A	France
PEFC	PEFC/07-32-37	
EPD	On request	
Higieniczny	HK/B/0149/03/2017	Poland

